

665 PRODUCT OVERVIEW



665 Membrane is 65 mil membrane composed of a self-adhering, polymer modified asphalt layer, laminated to a woven polypropylene backing. 665 Membrane is easy to work with and equally effective on bridges and pavements for waterproofing and crack control.

- \cdot 65 mil membrane: woven polypropylene backing with polymer modified asphalt adhesive
- · Compatible with asphalt and concrete pavements
- · Exceptional bond tpavement surface
- · Ease of installation available in widths from 12" to 48"
- · Minimal disruption to traffic
- · Moisture barrier protection
- · Reduces structural deterioration
- Extends pavement service life of overlay and bridge deck

Properties	Test Method	Marv Value
Thickness	ASTM D 1777 (using ½" presser foot)	65 mils.
Strip Tensile Strength	ASTM D 882	50 lbs./in. width
Grab Tensile Strength	ASTM D 4632	150 lbs.
Puncture Resistance	ASTM E154	200 lbs.
Permeance – Perms	ASTM E 96 (Method B)	0.05 max.
Elongation at break of fabric	ASTM D 4632	20 % min
Pliability at low temperatures -15EF	ASTM D 146 (Modified)	No cracks in fabric or rubberized asphalt

REV012224











