PRODUCT DATA SHEET

DETAIL TAPE

Adhesive Tape

MANUFACTURER

Polyguard Products, Inc. Ennis, TX 75119 (214) 515-5000 www.polyguard.com

PRODUCT DESCRIPTION BASIC USES

Detail Tape is used as detail strips on inside and outside corners, penetrations, control joints, cold joints and for patching damaged areas of the following products: 650 Membrane and PRM[™] waterproofing membranes.

COMPOSTITION & MATERIALS

Detail Tape is a strong, pliable, self-adhesive sheet consisting of a 4-mil cross-laminated, high-density polyethylene (HDPE) backing, bonded to 56 mils of rubberized-asphalt waterproofing compound.

Use Detail Tape for ambient and substrate surface temperatures of 25° F (5° C) and rising.

TECHNICAL DATA

See physical properties table.

INSTALLATION

The 650 Membrane and PRM[™] waterproofing membranes should be clean, dry and free of contaminates before application of the products Detail Tape.

Due to various uses of this product please see sheet membrane to be used for proper application instructions.

STORAGE AND HANDLING Material Handling

Membrane and accessories should be unloaded and stored carefully. Protect cartons and containers from weather, sparks, flames, excessive heat, cold and lack of ventilation. DO NOT stack membrane material higher than 5-feet vertically, nor double stack pallets. Store cartons on pallets and cover to prevent water damage. For best results, store membrane above 50° F (10° C) prior to application.

PRECAUTIONS

• The Liquid Adhesive is an industrial coating and would be harmful or fatal if swallowed. It is marked as red label from the stand-point of flash point.

- Prohibit flames, sparks, welding and smoking during application.
- Refer to product label for handling, using and storage precautions.
- Solvents could be irritating to the eyes; flush with water and contact physician.
- Avoid prolonged contact with skin and breathing of vapor or spray mist from liquid adhesive. In confined areas, use adequate forced ventilation, fresh air masks, explosion-proof equipment and clean clothing.
- Avoid solvent contact with light bulbs or other high temperature surfaces.

Ultraviolet Protection

Detail Tape is adversely affected by ultraviolet light. Cover the waterproofing system as soon as possible; DO NOT leave exposed to sunlight for over 30 days.

SAFETY

SDS documents for all Polyguard products can be obtained at our website <u>www.polyguard.com</u>. Call Polyguard Products, Inc. at (214) 515-5000 with questions.

WARRANTY

We, the manufacturer, warrant only that this product is free of defects, since many factors which affect the results obtained from this product are beyond our control; such as weather, workmanship, equipment utilized and prior condition of the substrate. We will replace at no charge product proved to be defective within twelve (12) months of purchase, provided it has been applied in accordance with our written directions for uses we recommended as suitable for this product. Proof of purchase must be provided.

TECHNICAL SERVICES

Technical assistance, information and Polyguard's products are available through a nationwide network of distributors and architectural representatives, or contact Polyguard Products, Inc. P.O. Box 755, Ennis, TX 75120-0755 Sales: (615) 217-6061•Tech Support: (214) 515-5000 Email: <u>archtech@polyguard.com</u> Website: <u>www.polyguard.com</u>

| PROPERTY | TEST METHOD | TYPICAL VALUE |
|--|--|--------------------|
| FILM COLOR | | Black |
| MEMBRANE THICKNESS | ASTM D 1000 | 60 mils |
| TENSILE STRENGTH - MEMBRANE | ASTM D 412 Modified Die C | 370 PSI |
| ELONGATION - ULTIMATE FAILURE OF RUBBERIZED ASPHALT | ASTM D 412 | 600% |
| TENSILE STRENGTH - FILM | ASTM D 882 | 7294 PSI |
| PERMEANCE | ASTM E 96 Method B | 0.022 Perms |
| CRACK CYCLING | ASTM C 836 Tested @-15° F (-26° C) | No effect |
| PEEL ADHESION | ASTM D 903 | 17 lbs./in. width |
| LAP PEEL ADHESION | ASTM D 1876 | 8.0 lbs./in. width |
| LOW TEMPERATURE FLEXIBILITY (-15°F) | ASTM D 1970 Modified | Pass |
| PLIABILITY | ASTM D 146 180° bend over 1" mandrel at -25° F (-32° C) | No effect |
| PUNCTURE RESISTANCE - MEMBRANE | ASTM E 154 | 69 lbs. |
| RESISTANCE TO HYDROSTATIC HEAD | ASTM D 5385 | 231 ft. |
| EXPOSURE TO FUNGI IN SOIL | GSA-PBS 07115 (16 weeks) | No effect |
| WATER ABSORPTION | ASTM D 570 | 0.1% |

| PACKAGING | PART NUMBER | UNIT SIZE |
|-------------|-------------|-----------|
| DETAIL TAPE | 650L12 | 12" x 50' |

DISCLAIMER: The information contained in this document is based on data and knowledge considered to be true and accurate at time of printing and is offered for the users' consideration, investigation and verification. Polyguard Products, Inc. cannot be held liable for errors made as a result of information herein. Changes and modifications can be made to this document without prior notice. No statement, recommendation or suggestion is intended for use which would infringe on patents or copyrights held by Polyguard Products, Inc.



P.O. Box 755, Ennis, TX 75120 PH: (214) 515-5000 <u>www.Polyguard.com</u> Detail Tape 04062023